











1200x1200mm



NERO-RISER&STRIP MATT/POLISHED





1200x1200mm









CHOCO MATT



CHOCO POILISHED



CHOCO MATT

1200x300mm



MATT/POLISHED

600x300mm

CHOCO POILISHED



СНОСО **MATT**

1200x1200mm



CHOCO-RISER&STRIP MATT/POLISHED







1200x1200mm

CHOCO-RISER&STRIP MATT/POLISHED








1200x1200mm

CREMA-RISER&STRIP MATT/POLISHED





















1200x1200mm



BLACK-RISER&STRIP MATT/POLISHED













Household Chemicals

TECHNICAL SPECIFICATION

THALAM VITRIFIED TILES SPECIFICATION						
CHARACTERISTICS	BIS STANDARD IS 15622:2007	THALAM VITRIFIED GVT/PGVT	TEST MENTHOD			
	DIMENSION & SURFACE Q	UALITY				
Deviation in Size	0.10%	±0.5mm	IS 13630-1			
Deviation in Thickness	5.0%	±0.3mm	IS 13630-1			
Straightness of Sides	0.10%	±1mm	IS 13630-1			
Rectangularity	0.10%	±1.2mm	IS 13630-1			
Surface Flatness						
Center Curvature	0.50%	±0.7mm	IS 13630-1			
Edge Curvature	0.50%	±0.7mm	IS 13630-1			
Warpage	0.50%	±0.7mm	IS 13630-1			
Surface Quality	Min. 95%	Min. 92%	IS 13630-1			
Glossiness(PGVT)		> 90% Reflection	Glossy Meter			
·	PHYSICAL PROPERT	ſΥ				
Bulk Density	2.2 g/cc	> 2.2 g/cc	IS 13630-2			
Water Absorption	Avg ≤ 0.08% / Local Max 0.1%	≥0.07%	IS 13630-2			
Breaking Strength	> 1300 N	> 1425 N	IS 13630-6			
Modulus of Rupture	Avg 35 / Local min 32	40 N/mm?	IS 13630-6			
Resistance to surface abrasion	Min Class II	Min Class III	IS 13630-11			
Resistance to deep abrasion	Max 140 mm}	Max 130 mm?	IS 13630-11			
Coefficient of Thermal Expansion	Max 6 X 106	Comply	IS 13630-12			
Themal Shock Resistance	Min 10 Cycle	No Damage	IS 13630-4			
Crazing Resistance	Min 4 Cycle @ 7.5 bar	Min 4 Cycles	IS 13630-5			
Frost Resistance	Required	Comply	IS 13630-9			
Moisture Expansion	0.02 mm/m	Nill	IS 13630-10			
Color Difference		No Change	IS 13630-3			
Impact Resistance	Min 0.55	Resistance	IS 13630-14			
Coefficient of Friction (Slipperiness Factor)	Company Declared	<0.5	IS 13630-10			
MOHS Hardness	Min.5	Matt<5	IS 13630-13			
	CHEMICAL PROPER	TY				
Stain Resistance	Glazed - Min Class 1 UnGlazed - Min Class 2	Min. Class - 3				
Resistance to Chemicals	Oligiazen - Milli Class Z					
Low Concentration	Glazed - Class AA Unglazed - Required	HCL(L) - GLB KOH-GLS Citric Acis-GB	IS 13630-7 IS 13630-8			
High Concentration	Required	GLC	IS 13630-7			

Glazed - Class AA

Unglazed - Required

GΑ

IS 13630-8

IS 13630-7

IS 13630-8



FULL BODY PACKING DETAILS

SIZE	THICKNESS (APPROX)	TILES PER BOX	COVERAGE AREA PER BOX(APPROX)	WT.OF BOX (APPROX)
600X1200mm	10.0mm	2Pcs.	1.44 Sq.m.	31.0 kgs.
600X600mm	8.5mm	4Pcs.	1.44 Sq.m.	28.0 kgs.
300X600mm	8.5mm	5Pcs.	0.90 Sq.m.	17.5 kgs.
298x1200mm (STEPS)	10.0mm	3Pcs.	1.07 Sq.m.	24.0kgs.
198x1200mm (STRIP & RISER)	10.0mm	3Pcs.	0.71 Sq.m.	16.0kgs.





49/1A, 1B2&2B, Senkottai Vilakku, Sivagangai Road, Madurai, Tamilnadu, India - 625020.